



ERL GRUP

REKLAM, PLASTİK, MAKİNA, KİMYA, SAN. DİŞ. TİC. LTD. ŞTİ.

200 GSM TARPAULIN FABRIC

TECHNICAL INFORMATION	TESTING METHOD	UNIT	WARP	WEFT	TOLERANCES
RAW MATERIAL			HDPE	HDPE	
YARN/ 10 CM	ISO 7211-2	10/ cm	55	60	± 1
DENIER	ISO 2060	Td.	900	900	$\pm \% 5$
YARN WIDTH		mm	2	3	$\pm \% 5$
TENSIL STRENGTH		kg/5cm	85	80	$\pm \% 5$
ELONGATION STRENGTH	ISO 5081	%	15	13	min
U.V.		%	1		min
FABRIC WEIGHT	ISO 3081	gr/ m ²	120		$\pm \% 2$
COATING WEIGHT		gr/ m ²	80		$\pm \% 5$