



ERL GRUP

REKLAM, PLASTİK, MAKİNA, KİMYA, SAN. DIŞ. TİC. LTD. ŞTİ.

ERL GRUP PVC BRANDA TEKNİK BİLGİ FORMU

PVC TARPAULIN TECHNICAL DATA SHEET

ÜRÜN TANIMI :	620-630 PVC BRANDA		
PRODUCT DESCRIPTION :	620-630 TRUCK TARPAULIN		
TEKNİK ÖZELLİKLER TECHNICAL SPECIFICATIONS	STANDARTLAR STANDARDS	BİRİM UNIT	DEĞER VALUE
ANA KUMAŞ : BASE FABRIC :	DIN 60 001		100% PES
İPLİK TÜRÜ : YARN TYPE :	DIN EN ISO 2060	POLYESTER	1100 DTX
DOKUMA SIKLIĞI : WEAVING CONSTRUCTION :			8X8 (20X20)
BİRİM ALAN KÜTLESİ : WEIGHT :	TS 1534 EN ISO 2286-2 DIN EN ISO 2286-2	gr/m ² qr/m ²	630 ± 5
GENİŞLİK : WIDTH :		cm cm	150-250-300-320 (MÜŞTERİ İSTEĞİNE BAĞLI) (DEPENDS ON CLIENTS REQUEST)
RULO UZUNLUĞU : ROLL LENGTH :		m m	50-250 (MÜŞTERİ İSTEĞİNE BAĞLI) (DEPENDS ON CLIENTS REQUEST)
ÜRÜN ÇEŞİTLİLİĞİ : SURFACE TREATMENT :			PARLAK-MAT-DESENİLİ GLOSSY-MATT-EMBOSS
SICAKLIK DİRENCİ : TEMPERATURE RESISTANT :	DIN EN 1876-1	°C	-30
SICAKLIK DİRENCİ : TEMPERATURE RESISTANT :	IVK/Pkt.5	°C	+70
KOPMA DİRENCİ (çözü/atku) : TENSILE STRENGTH (warp/weft):	TS 2008 EN ISO 1421 EN ISO 1421	N/5cm	2100 / 2000
YIRTILMA DİRENCİ (çözü/atku) : TEAR STRENGTH (warp/weft):	TS EN ISO 4674-1 EN ISO 4674-1	N	200 / 190
YAPIŞMA : ADHESION :	TS EN ISO 2411 EN ISO 2411	N/5cm	40
RENK HASLIGI : COLOUR FASTNESS :	BS EN ISO 105-B02		6
EKSTRA ÖZELLİK: EXTRA TREATMENT:	ACRYLIC, SILVER, PVDF LAC		(TALEP EDİLİRSE) (IF DEMANDED)
YANMAZLIK : FLAMMABILITY (FR) :	DIN 4102-1B2 / NF P 92-507		B2 / M2/B1 (TALEP EDİLİRSE)

ATTENTION! The above Technical Data has an arithmetical average deviation ratio as +/- 5%.